

Perdüre E10

100% solids epoxy sealer/binder

düraamen

engineered to perform

DESCRIPTION

Perdüre E10 is a 100% solids, multipurpose epoxy binder for Düraamen self leveling mortar and quartz systems. This all purpose epoxy resin is characterized as an excellent general purpose material with good clarity and color retention. It is essentially odorless and therefore can be applied in occupied areas.

ADVANTAGES

- Good troweling properties when used with Duraamen self leveling epoxy mortar and quartz systems
- Excellent color retention when used as a topcoat with Düraamen flooring systems
- Good troweling properties when used in mortar systems
- Low odor for use in occupied areas
- Available in fast cure systems
- USDA approved for food handling applications

SUBSTRATE REQUIREMENTS

- Bonding surfaces must be sound, clean, and free from standing water
- Substrate temperature must be a minimum of 500F
- Substrate must be free of dirt, waxes, curing agents and other foreign materials
- Pigmented version should not be used as a top coat

COMPOSITION

- 100% solids amine cured epoxy resin

APPLICATION

Surface Preparation is the most critical portion of any successful resinous flooring system application. All substrates must be properly prepared as outlined in Düraamen Technical Bulletin # 1. Work must be performed by trained or experienced contractors or maintenance personnel. The Düraamen Company's service department is pleased to answer any technical questions.

INSTALLATION

It will vary with the application purpose and method.

For complete installation instructions, contact your Düraamen representative.

CLEAN UP

Clean skin with soap and water. Tools and equipment should be cleaned with Xylene or Lacquer thinner. Consult MSDS for safety and health precautions.

COVERAGE

Perdüre E10 yields 200ft² per gallon at 5-6 mils film thickness.

AVAILABILITY

Perdüre E10 is available throughout the United States and Canada. Contact Düraamen representative in your area for details.

MAINTENANCE


After completing the application of Perdüre E10, the installer should provide the owner with maintenance instructions. If floors become slippery due to animal fats, oil, grease, or soap film, clean and rinse thoroughly. Perdüre E10 is easily cleaned with neutral soaps or detergents. Routine mechanical scrubbing is recommended for all surfaces having a non-skid texture. Waxing is optional. Long periods of heavy traffic may cause wear patterns necessitating application of a finish coat.

COLOR SELECTION

Perdüre E10 is available in Clear or Standard Colors. Custom colors are available subject to laboratory approval, minimum quantity, lead time for production, and increased cost.

TECHNICAL SERVICE

Düraamen Building & Allied Products, Inc. provides services and consultations on material selection, specification, troubleshooting, and other information on the proper repair and protection of concrete surfaces.



düraamen engineered products, inc.

116 West 23rd Street, 5th Floor, New York, NY 10011 | duraamen.com | info@duraamen.com | 1.866.835.6595

TECHNICAL DATA

Viscosity @ 75°F	950cps
Mixing Ratio	4 parts A to 1 parts B by volume
Solids Content	100% Solids by volume
Volatile Organic Content	-0-
Gloss, 60°F	85-100
Weight Per gallon	9.00-9.50 pounds per gallon, mixed
VOC	Zero

CURE/DRY TIME

Pot Life	30-40 minutes
Dry to Touch	6-8 hours @ 75°F
Re-Coat (regular cure)	10-12 hours @ 75°F
Re-coat (fast cure)	4-6 hours @ 75°F
Full cure, max. resistance	5 days

PERFORMANCE PROPERTIES

Tensile Strength ASTM D638	8500psi
Elongation ASTM D638	5.5%
Adhesion to Metal	2500psi
Adhesion to Concrete ACI403	350psi (concrete fails)
Hardness ASTM D2240	80 (Shore D)
Service Temperature MILD 3134F	160F (immersion) 185F (dry heat)
Abrasion resistance ASTM C501	35-40 mg loss (CS-17 wheel, 1kg load, 1000loads)
Impact Resistance, MILD 3134F	Withstands 16ft/lb – no cracking, delamination or chipping
Indentation MILD 3134F	Withstands 2000lb/sq.in for 30min without indentation
Water Absorption ASTM D 670 63 (24hr immersion)	0.10% maximum
Flexural Strength, ASTM D790	8000psi
Compressive Strength, ASTM D 695	11000psi

CHEMICAL RESISTANCE


REAGENT	RATING
Acetic Acid – 5%	L
Acetone	L
Bleach	L
Citric Acid – 30%	R
Crude Oil	R
Diesel Fuel	R
Ethylene Glycol	R
Fatty Acids	L
Gasoline	R
Hydrochloric Acid-15%	R
Lactic Acid -15%	R
MEK	L
Nitric Acid – 10%	R
Skydrol	R
NaOH-50%	R
Sulfuric Acid-20%	R
Toluene	R
Urea	R
Vinegar	L
Xylene	R

R- Recommended for continuous service

L – Limited use, occasional spills

WARRANTY

Information regarding Duraamen products is based upon extensive research provided by the supplier of the raw materials. By making such information available, Duraamen Engineered Products Inc. does not assume any liability beyond express terms of our standard limited material warranty. Duraamen Engineered Products does not warrant the accuracy or completeness of any such information, whether conveyed orally or in writing, but to the best of our knowledge believe it to be accurate. We reserve the right at any time and without notice to update or improve our products and process for the intended use or application. Duraamen Engineered Products (Duraamen) warrants for a period of one (1) year that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Duraamen. If any product fails to meet this warranty, the liability of Duraamen will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Duraamen within 1 (one) year of delivery of materials. Duraamen may in its discretion refund the price received by Duraamen in lieu of replacing the material. No customer, distributor, or representative of Duraamen is authorized to change or modify the published specifications of this warranty in anyway. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Duraamen reserves the right to inspect the non-conforming material prior to replacement EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OR MERCHANTABILITY OR FITNESS FOR PURPOSE. DURAAMEN'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND DURAAMEN SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



duraamen engineered products, inc.

116 West 23rd Street, 5th Floor, New York, NY 10011 | duraamen.com | info@duraamen.com | 1.866.835.6595