

Macrylex H00

Dibenzoyl peroxide hardener

DESCRIPTION

Macrylex H00 is a dry white powder made up of 50% BPO, Dibenzoyl Peroxide. It must be mixed thoroughly with Macrylex resins before adding other fillers and/or aggregates to ensure the hardening of the mixed materials. Any exception to this mixing sequence must be confirmed with Duraamen Technical Representative.

Macrylex H00 is soluble in Macrylex resin. After mixing the powder into the reactive resin the reaction initiates the polymerization reaction that leads to the hardening process of the floor system.

TECHNICAL DATA

Appearance	Sandy, White Dry Powder
Content of Dibenzoyl Peroxide and Dicyclohexyl Phthalate	Approximately 50%
Self-accelerating Decomposition Temperature (SADT)	140°F
Self-Ignition Temperature	>680°F
Solubility	Not soluble in water

PACKAGING

8 vol oz	8 vol. oz jar
5lb	1 gallon jar
15lb	3 gallon jar
55lb	1 box

WARRANTY

Information regarding Duraamen products is based upon extensive research provided by the supplier of the raw materials. By making such information available, Duraamen Engineered Products Inc. does not assume any liability beyond express terms of our standard limited material warranty. Duraamen Engineered Products does not warrant the accuracy or completeness of any such information, whether conveyed orally or in writing, but to the best of our knowledge believe it to be accurate. We reserve the right at any time and without notice to update or improve our products and process for the intended use or application. Duraamen Engineered Products (Duraamen) warrants for a period of one (1) year that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Duraamen. If any product fails to meet this warranty, the liability of Duraamen will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Duraamen within 1 (one) year of delivery of materials. Duraamen may in its discretion refund the price received by Duraamen in lieu of replacing the material. No customer, distributor, or representative of Duraamen is authorized to change or modify the published specifications of this warranty in anyway. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Duraamen reserves the right to inspect the non-conforming material prior to replacement EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OR MERCHANTABILITY OR FITNESS FOR PURPOSE. DURAAMEN'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND DURAAMEN SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

PROCESSING

Macrylex H00 must only be mixed immediately before the application of Macrylex Resins. Fillers and aggregates are added after the hardener is added and mixed. It is important to follow the mix ratio chart for each resin pertaining to temperature and desired set time, refer to the individual resin product data sheets and the Macrylex H00 Mixing Chart document for the correct amount of hardener. The amount of hardener needed depends on the type of resin being used and the temperature.

SAFETY NOTES

Macrylex H00 is an oxidizing agent that violently decomposes under the influence of heat or when in contact with reducing agents. **DO NOT MIX WITH ACCELERATORS**. Store separately from the Macrylex resins. Review MSDS information thoroughly.

STORAGE

Store in tight containers in dry environments below 80°F.

