

Perdure P72

Polyaspartic polyurea topcoat

düraamen
engineered to perform

DESCRIPTION

Perdure P72 is a new generation fast-curing, two component, polyaspartic aliphatic polyurea formulated to be used as a sealer or topcoat for interior or exterior use over properly prepared concrete or resinous flooring systems. It has excellent penetration and bond strength to properly prepared surfaces, UV resistant, and abrasion, impact, and wear resistant.

ADVANTAGES

- Self-priming, excellent penetrating to achieve excellent bond strength
- Superior abrasion, impact and wear resistance
- Excellent hot tire pickup resistance
- UV resistance, does not turn 'yellow' or 'amber'
- Reduces floor care, cleaning and maintenance costs
- Low temperature cure

IMPORTANT CONSIDERATIONS

- Substrate temperature must be a minimum of 50°F
- Substrate must be free of dirt, waxes, curing agents and other foreign materials
- Do not apply over damp or wet substrates
- Avoid applications on surfaces with active moisture vapor transmission
- Very fast set (short working time)

COMPOSITION

- Two component polyaspartic polyurea

APPLICATION

Surface Preparation is the most critical portion of any successful resinous flooring system application. All substrates must be properly prepared as outlined in Duraamen's Technical Bulletin # 1. Work must be performed by trained or experienced contractors or maintenance personnel. The Duraamen Company's service department is pleased to answer any technical questions.

INSTALLATION

Perdure P72 is a two component system. Mix Part A and Part B in equal parts (1:1) using a clean, dry container. Stir gently using a mechanical stirrer, avoiding over mixing or creating vortex that could introduce moisture. Do not mix below the dew point, which will shorten the pot life. No induction time is required prior to use. After mixing the Parts A & B, Perdure P72 has a working time of 15 minutes at a temperature of 70°F and 50% RH. At higher temperatures and humidity the working time can be shorter.

An industrial grade, phenolic resin core with a synthetic nap (1/4" or 3/8" nap, 18" width) roller is recommended for application.

CLEAN UP

Clean skin with soap and water. Tools and equipment should be cleaned with Xylene or Lacquer thinner. Consult MSDS for safety and health precautions.

COVERAGE

Perdure P72 yields 200-250ft²/gallon at 5-6mil thickness

COLOR SELECTION


Perdure P72 is available in clear but it can be pigmented upon request which may require longer lead time and increased cost.

AVAILABILITY

Perdure P72 is available throughout the United States and Canada. Contact Duraamen representative in your area for details

MAINTENANCE

After completing the application of Perdure P72, the installer should provide the owner with maintenance instructions.



düraamen engineered products, inc.

116 West 23rd Street, 5th Floor, New York, NY 10011 | duraamen.com | info@duraamen.com | 1.866.835.6595

TECHNICAL SERVICE

Duraamen Engineered Products, Inc. provides services and consultations on material selection, specification, troubleshooting, and other information on the proper repair and protection of concrete surfaces

TECHNICAL DATA

Viscosity @ 75°F	250 – 300cps
Mixing Ratio	1:1
Solids Content	72% by volume
VOC	0
Tensile Strength, ASTM D638	5000
Abrasion Resistance, ASTM D968	30liters sand/1 dry mil

CURE/DRY TIME

Pot Life	20 minutes
Dry to Touch	2.5 hours @ 75°F
Re-Coat	4 hours @ 75°F
Light Traffic	4 – 5 hours @ 75°F
Heavy traffic	48 hours

CHEMICAL RESISTANCE

REAGENT	RATING
Acetic Acid – 5%	L
Acetone	L
Ammonium Hydroxide 38%	R
Beer	R
Brake Fluid	L
Bleach	L
Citric Acid – 30%	R
Citric Acid – 40%	L
Crude Oil	R
Diesel Fuel	R
Ethylene Glycol	R
Fatty Acids	L
Gasoline	R
Hydrochloric Acid – 15%	R
Lactic Acid – 15%	R
Lactic Acid – 50%	L
Methyl Ethyl Ketone	L
Nitric Acid – 10%	L*
Orange Juice	R
Peroxide – 35%	L
Phosphoric Acid – 85%	L
Iodine	L
Skydrol	R
Sodium Hydroxide – 50%	R
Sulfuric Acid – 20%	R
Toluene	L
Urea	R
Vinegar	R
Xylene	L
Xylene	R


R-Recommended for continuous service

L-Limited Recommendation, occasional spills

*-May cause slight stain or discoloration

WARRANTY

Information regarding Duraamen products is based upon extensive research provided by the supplier of the raw materials. By making such information available, Duraamen Engineered Products Inc. does not assume any liability beyond express terms of our standard limited material warranty. Duraamen Engineered Products does not warrant the accuracy or completeness of any such information, whether conveyed orally or in writing, but to the best of our knowledge believe it to be accurate. We reserve the right at any time and without notice to update or improve our products and process for the intended use or application. Duraamen Engineered Products (Duraamen) warrants for a period of one (1) year that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Duraamen. If any product fails to meet this warranty, the liability of Duraamen will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Duraamen within 1 (one) year of delivery of materials. Duraamen may in its discretion refund the price received by Duraamen in lieu of replacing the material. No customer, distributor, or representative of Duraamen is authorized to change or modify the published specifications of this warranty in anyway. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Duraamen reserves the right to inspect the non-conforming material prior to replacement EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OR MERCHANTABILITY OR FITNESS FOR PURPOSE. DURAAMEN'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND DURAAMEN SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



duraamen engineered products, inc.

116 West 23rd Street, 5th Floor, New York, NY 10011 | duraamen.com | info@duraamen.com | 1.866.835.6595